TYPE OF LEATHER : Cow Oil Pull Up **THICKNESS :** 1.4 - 1.6 mm

RETANNING - DYEING - FATLIQUORING					
OPERATIONS	**PRODUCT**	**℃**	**%**	**Run**	**Remarks**
Washing	Water	30	200		
	Sintol ALX		0.5		
	Acetic Acid		0.5	30	Drain
Neutralisation	Water	30	150		
	Syntan NP		1.5		
	Sodium Formate		1.5	45	
+	Sodium Bi Carbonate		0.5	15	pH 4.8 - 5.0, D/W/D
Retanning	Water	30	150		
Dyeing	Syntan PRS		2.5	20	
Fatliquoring +	Syntan NX		4.0		
	Syntan PMX		2.0		
	G S Powder		4.0		
	Qubracho		4.0		See Remarks, D/W/D
	Chestnut		2.0		
	Syntan R - MF		4.0		(15+15+30), D/W/D
	Maradol C		1.0	90	
+	Brown CB		1.3		
	Brown BSI		0.7	45	Check ø
+	Formic Acid		0.5	30	Drain
	Water	60	100		
	Luber SN		2.0		
	Luber NF		2.0		
	Sintol SF		2.0	45	
	G. S. Powder		1.0	10	
+	Formic Acid		1.5	30	10+10+10, D/W/D

MACHINE OPERATIONS : Pile O/N., Samm, Set, Vd, Hang Dry, Stake, Buff.

REMARKS : Run – Time in Minutes

Code :

D/W/D = Drain / Wash / Drain Chk = Check ø = Cross Section + = Add
Run = Time in Minutes Pdr = Powder Vd = Vacuum Dry L O/N = Leave Over Night

Our technical advise - whether verbal, in writing or by way of trials - is given in good faith but without warranty and this also applies where proprietary rights of third party are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and uses. The application, use and processes and processing of the product are beyond our control and therefore entirely are your own responsibility. We will off course provide the product of consistent quality with in the scope of our General Conditions of Sales and Deliveries.