

HARYANA

TYPE OF LEATHER : Cow

ARTICLE : Shoe Upper

TYPE OF FINISH : Oil Pull Up

COLOUR : Brown

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Pullol LMC	100					1. 1 r/c, Leave Over Night, Plane plate at 100 °C / 50 Kg., 1 light spray, dry well.
2	Glaze Top N		75	100			
3	Protop 18		75	100			
4	Dye Solution		25				
5	Urez 899		100				
6	Water		725	800			
7							2. 2 – 3 light x coats,
8							
9							3. 1 x coat, Fix, Dry well Fix & Contilux at 100 °C / 40 Kg.
10							
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							
25							

APPLICATION: Buff twice with 320 grit paper on both sides before finishing.

REMARKS:

Code:

Pn = Hair Cell Print Po = Polish P = Plate •C/Bar M = Dry Drum (Mill)
 Pr = Emboss •C RB = Rebuff Vd = Vacuum Dry O/N = Over Night

Our technical advise - whether verbal, in writing or by way of trials - is given in good faith but without warranty and this also applies where proprietary rights of third party are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and uses. The application, use and processes and processing of the product are beyond our control and therefore entirely are your own responsibility. We will of course provide the product of consistent quality with in the scope of our General Conditions of Sales and Deliveries.