

## HARYANA

**TYPE OF LEATHER** : Sheep

**ARTICLE** : Lining

**TYPE OF FINISH** : Resin Finish

**COLOUR** : Natural

<b>FINISHING FORMULATION &amp; PROCESS</b>							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Urez 899	150	50				1. 1 X Coat, plate at 80°C, 50 kg/ sq.cm.
2	IPA	100					
3	Water	400	500	200			
4	Nano Pigment Mix		100				2. 2 X Coats, Dry well, fine Hair Cell Plate at 80° C, 50 Kg, 2 – 3 X Coats.
5	Protop 18		50				
6	Filler WTD		50				
7	Filler 12 / 61		50				3. 1 X Coat, Dry well, Contilux.
8	Acril-m X 79/60		100				
9	Acril-m S 8/1		100				
10	Aquasol W 100			100			
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							
25							

**APPLICATION:**

**REMARKS:**

**Code:**

Pn = Hair Cell Print      Po = Polish      P = Plate •C/Bar      M = Dry Drum (Mill)  
 Pr = Emboss •C      RB = Rebuff      Vd = Vacuum Dry      O/N = Over Night

Our technical advise - whether verbal, in writing or by way of trials - is given in good faith but without warranty and this also applies where proprietary rights of third party are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and uses. The application, use and processes and processing of the product are beyond our control and therefore entirely are your own responsibility. We will of course provide the product of consistent quality with in the scope of our General Conditions of Sales and Deliveries.