

## LUBER G 60

LUBER G 60 is a replacement fatliquor for sulphited sperm oil based product with similar characteristics.

### CHARACTERISTICS:

<b>Appearance</b>	: Light Brown Liquid
<b>Base</b>	: Sulphited Synthetic Sperm Oil Substitute
<b>Active Content</b>	: 60 ± 1%
<b>pH (1:10)</b>	: 8.5 ± 0.5
<b>Charge</b>	: Anionic
<b>Stability</b>	: Very Good
<b>Lightfastness</b>	: Good
<b>Shelf Life</b>	: Twelve months

LUBER G 60 imparts good handle, body & softness to the treated leathers. It may also be used for the production of pastel shade leathers and has no tendency to discolour the leather.

LUBER G 60 is fairly stable to acids, salts and hard water & can be used in pre-fatliquoring and rechroming stages of process.

Good penetrating power of LUBER G 60 is beneficial in producing soft leathers for light garments and gloving etc.

### EMULSION INSTRUCTIONS:

To the required quantity of LUBER G 60 add slowly, three times of its own weight of water at 60°C, while stirring.

CONVENTIONAL  
FATLIQUORS

### SUGGESTED APPLICATIONS:

a) Cow Nappa (Upper)	Pre-fatliquoring	1.0 %	LUBER G 60
	Fatliquoring	3.0 %	LUBER G 60
		3.0 %	Nouvel LS-55
		6.0 %	Nouvel-PK
		3.0 %	Maradol-C
		3.0 %	Luber-SAS
b) F/Cr. Goat (Upper)	Rechrome	1.0 %	Maradol-C
	Fatliquoring	1.5 %	LUBER G 60
		1.5 %	Nouvel LS-55
c) F/Cr. Sheep Garment Nappa	Rechrome	1.5 %	LUBER G 60
	Fatliquoring	2.0 %	LUBER G 60
		4.0 %	Nouvel LS-55
		3.0 %	Maradol-C
		5.0 %	Nouvel-PK

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.