

# HARYANA

ACRYLICS

## ACRIL-M M 701

Self cross linking soft micro binder for highly natural look on leather.

### CHARACTERISTICS OF EMULSION

Appearance	: Milky Semi-Transparent Emulsion
Nature	: Polyacrylate Dispersion
Solid Content	: 20 ± 1%
pH (10% Sol.)	: 8.0 ± 0.5
Density	: 1.02
Charge	: Anionic
Gloss	: Bright
Mechanical stability	: Good
Reaction with ammonia	: None

### CHARACTERISTICS OF FILM

Appearance	: Transparent
Elongation	: 05 (1 Min. – 10 Max.)
Gloss	: 09 (1 Matt – 10 Glossy)
Shore Hardness	: 03 (1 Softest – 10 Hardest)
Light fastness	: Good
Cold-crack resistance	: Good

**ACRIL-M M 701** is a micro-fine self cross linking acrylic binder of soft nature.

**ACRIL-M M 701** is well suited for producing high quality leather like Nappas and Uppers with natural look.

### SUGGESTED APPLICATIONS:

Semi Anilene Sheep Nappa	:	20 parts	Pigment - Nano Series
		50 parts	Dye solution - Novolene Series
		30 parts	Wax 16/S
		50 parts	GlazEx 10
		600 parts	Water
		100 parts	<b>ACRIL-M M 701</b>
		50 parts	Urez 898
Softy Uppers	:	100 parts	Acril-m X 858
		80 parts	Pigment - Nano Series
		20 parts	Dye solution - Novolene Series
		30 parts	Protop 18
		50 parts	Filler 50
		50 parts	Filler 12 / 61
		470 parts	Water
		100 parts	<b>ACRIL-M M 701</b>
	100 parts	Acril-m X 858	
	100 parts	Urez 899	

**Note :** Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.