

HARYANA

ACRYLICS

ACRIL-M S 60

Soft thermo cross linkable binder of high concentration for the finishing of heavily buffed leathers.

CHARACTERISTICS OF EMULSION

Appearance : White Emulsion

Nature : Polyacrylate Dispersion

Solid Content : 48 ± 1%

pH (10% Sol.) : 6.5 ± 0.5

Density : 1.06

Charge : Anionic

Gloss : Bright

Mechanical Stability : Good

Reaction with Ammonia : Non-thickening

CHARACTERISTICS OF FILM

Appearance : Dull, Straw-coloured

Elongation : 07 (1 Min. – 10 Max.)

Gloss : 09 (1 Matt – 10 Glossy)

Shore Hardness : 04 (1 Softest – 10 Hardest)

Light Fastness : Good

Cold-crack Resistance : Good

ACRIL-M S 60 is a thermo cross linking type of binder having high solid content. This means the product is well suited for finishing of well buffed leather, either alone or alongwith Acril-m S 66.

SUGGESTED APPLICATIONS:

Buffalo C/G	:	120 parts	Pigment - Nano Series
		50 parts	Filler WTD
		50 parts	Glaze Top N
		20 parts	Modifier WS
		100 parts	Filler 12 / 61
		400 parts	Water
		100 parts	ACRIL-M S 60
		100 parts	Acril-m X 01
		75 parts	Urez 899
		20 parts	Luber 150
Softy Uppers	:	100 parts	Pigment - Nano Series
		50 parts	Filler 50
		30 parts	Protop 18
		550 parts	Water
		125 parts	ACRIL-M S 60
		75 parts	Acril-m X 858
		50 parts	Urez 894
		20 parts	Luber 205

IMPORTANT: PROTECT FROM FREEZING

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.