

HARYANA

ACRYLICS

ACRIL-M S 66

Polyacrylate Dispersion of micro fine particles and soft film. Provides good defect coverage & can be used in pre-bottoming, bottoming & intermediate coats.

CHARACTERISTICS OF EMULSION

Appearance	: Semi Transparent Milky Emulsion
Nature	: Polyacrylate in Water
Charge	: Anionic
Solid Content	: 20 ± 1%
pH (10% Sol.)	: 8.5 ± 0.5
Mechanical Stability	: Good
Reaction with Ammonia	: Does not Thicken
Shelf Life	: Six months

CHARACTERISTICS OF FILM

Appearance	: Thin & Slightly Opaque
Elasticity	: Soft & Elastic
Tack Level	: Negligible
Light Fastness	: Excellent
Cold-crack Resistance	: Excellent

ACRIL-M S 66 is a soft & penetrative micro binder which forms a slightly opaque film on drying. It does not alter the softness of leather while provides good masking of defects.

ACRIL-M S 66 is very low tack binder which provides excellent waxy touch to the treated leather thus improving the smoothness and uniformity of finish. It can be combined with other acrylic binders for the finishing of various types of leathers and is specially suitable for the finishing of sheep nappa.

SUGGESTED APPLICATIONS:

Sheep Nappa	:	100 parts	Pigment – Nano Series
		30 parts	Dye Solution – Novolene Series
		40 parts	Filler 50
		30 parts	Filler 12 / 61
		120 parts	ACRIL-M S 66
		90 parts	Acril-M X 858
		60 parts	Urez 899
		20 parts	Glaze Top N
		510 parts	Water
Cow Dry Milled	:	120 parts	Pigment – Nano Series
		50 parts	Filler 12/61
		50 parts	Protop SP
		50 parts	Filler WTD
		100 parts	ACRIL-M S 66
		100 parts	Acril-m S 60
		50 parts	Urez 891
		480 parts	Water

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.