

## HARYANA

ACRYLICS

### ACRIL-M X 79/60

Medium Soft Acrylic Binder for use as main component for finishing of heavily corrected grain leathers.

#### CHARACTERISTICS OF EMULSION

Appearance	: White Milky Emulsion
Nature	: Polyacrylate Dispersion
Solid Content	: 36 ± 1%
pH (10% Sol.)	: 5.0 ± 0.5
Charge	: Anionic
Density	: 1.04
Mechanical Stability	: Good
Reaction with Ammonia	: No Change

#### CHARACTERISTICS OF FILM

Appearance	: Transparent-yellowish
Elongation	: 05 (1 Min. – 10 Max.)
Gloss	: 08 (1 Matt – 10 Glossy)
Shore Hardness	: 04 (1 Softest – 10 Hardest)
Light Fastness	: Good
Cold-crack Resistance	: Very Good

ACRIL-M X 79/60 is acrylic binder for heavily corrected grain leather.

#### SUGGESTED APPLICATIONS:

Corrected Grain	:	100 parts	Pigment - Nano Series
		100 parts	Acril-m X 858
		100 parts	<b>ACRIL-M X 79/60</b>
		50 parts	Glaze Top EC
		50 parts	Filler WTD
		50 parts	Filler 12 / 61
		50 parts	Urez 899
	500 parts	Water	
Smooth Finish	:	150 parts	Pigment - Nano Series
		100 parts	Acril-m S 60
		150 parts	<b>ACRIL-M X 79/60</b>
		100 parts	Urez 894
		50 parts	Glaze Top N
		80 parts	Filler 12 / 61
		50 parts	Filler WTD
		20 parts	Luber 105
		80 parts	Water
		20 parts	Resina 60

#### IMPORTANT: PROTECT FROM FREEZING

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.