

HARYANA

AQUASOL W 200

Self-emulsifiable top coat finishing lacquer. Compatible with solvent & water with silicon touch.

PROPERTIES:

Appearance	:	Transparent Light Straw Coloured
Solid Content	:	28 ± 1%
pH (10% Sol.)	:	7.5 ± 0.5
Flexibility	:	Good
Shelf Life	:	Six months

AQUASOL W 200 can be emulsified with water (max. 1:2) or diluted with solvent. The water emulsion has good gloss and rubfastness which improves considerably if used in solvent system.

AQUASOL W 200 can be added to other emulsion lacquers to improve gloss and other physical properties. It imparts silky feel to the leather and hence, further addition of feel modifiers may not be necessary.

AQUASOL W 200 may also be diluted with thinner for better gloss and fastness properties.

EMULSION INSTRUCTION:

To the required quantity of **AQUASOL W 200** add slowly double quantity of soft warm water, while stirring constantly.

SUGGESTED APPLICATIONS:

Glossy Top Coat	:	100 parts	AQUASOL W 200
		200 parts	Water
High Gloss Top Coat	:	100 parts	AQUASOL W 200
		200 parts	Butyl Acetate

LACQUERS

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.