

HARYANA

FILLER 89 C

Soft, non-yellowing Cationic filler based on Cellulose Acetate Butyrate.

PROPERTIES :

Appearance	:	Milky White Liquid
Base	:	Aqueous Cationic Wax
Solid Contents	:	16%
pH (10% Sol.)	:	4.5 ± 0.5
Shelf Life	:	Six months

Filler 89 C is Aqueous Cationic Wax for base coat applications where it helps in hiding / masking of defects & improves selection.

Filler 89 C does not affect natural look.

Filler 89 C provides soft warm handle & improves hold up, filling and coverage.

Filler 89 C can be used in other coats as feel modifier.

SUGGESTED APPLICATIONS :

C/G Buff Nappa	:	100 parts	FILLER 89 C
Base Coat	:	100 parts	Brillento 91 KT
	:	300 parts	Water

One wet spray, age, plate at 80 °C and 50 kg./cm². Finish in the normal way.

FILLERS,
WAXES &
MODIFIERS

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.