

**GLAZE TOP LM 58**

Hard protein binder suitable for leather finishing.

**PROPERTIES:**

<b>Appearance</b>	: Straw like (can change the colour)
<b>Basic Ingredients</b>	: Casein
<b>Solid Content</b>	: 10 ± 1%
<b>pH (10% Sol.)</b>	: 8.5 ± 0.5
<b>Nature</b>	: Hard Protein
<b>Charge</b>	: Anionic
<b>Shelf Life</b>	: Six months

**PROTEIN  
BINDERS**

**GLAZE TOP LM 58** is a hard protein binder for use as final top coat in glazed finishes. It may also be incorporated in resin finish to reduce the tack of the treated leathers and improve the print retention.

**GLAZE TOP LM 58** imparts good touch as top coat. Its use in glaze finish provides high gloss and very good dry & wet rubfastness in the leathers.

**GLAZE TOP LM 58** may be used in the glazing season in a small quantity to improve the rubfastness of the finish. It can be fixed in the usual manner with fixatives like formaline or crosslinkers.

**SUGGESTED APPLICATIONS:**

<b>Glaze Finish (Top Coat)</b>	: 150 parts	<b>GLAZE TOP LM 58</b>
	50 parts	Protop 18
	3 parts	Xama 7 (or any other crosslinkers)
	750 parts	Water
<b>Glaze Finish (Season Coat)</b>	: 30 parts	<b>GLAZE TOP LM 58</b>
	970 parts	Normal Season Mixture
<b>Resin Finish</b>	: 40-60 parts	<b>GLAZE TOP LM 58</b>
	950 parts	Normal Season Mixture

**Note :** Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.