

HARYANA

HICALAC 319

Cross linkable lacquer emulsion to provide good rubfastness, high gloss and heat resistance.

PROPERTIES:

Appearance	: White Emulsion
Solid Content	: 19 ± 1%
pH (1:1)	: 8.5 ± 0.5
Flexibility	: Medium
Gloss	: High
Heat Resistance	: High
Shelf Life	: Six months

HICALAC 319 is a nitrocellulose based top coat lacquer emulsion which on application shows better heat resistance properties, good fastness, anchorage and scuff resistance.

Leathers treated with **HICALAC 319** may be plated at relatively higher temperature.

Compatibility of dye solution & feel modifiers should be pre-checked before addition to **HICALAC 319**.

EMULSION INSTRUCTION:

To the required quantity of **HICALAC 319** slowly add equal quantity of soft water with constant stirring.

SUGGESTED APPLICATIONS:

Sheep Nappa	:	100 parts	HICALAC 319
		100 parts	Water
Softy Uppers	:	100 parts	HICALAC 319
		50 parts	Water

LACQUERS

Note : Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.