

GLAZE TOP LM 58

Characteristics of Emulsion

| | |
|-------------------|-------------------------------------|
| Appearance | : Straw like (can change the color) |
| Basic Ingredients | : Casein |
| Solid Content | : 10 ± 1% |
| pH (10% Sol.) | : 8.5 ± 0.5 |
| Nature | : Hard Protein |
| Film Appearance | : Transparent, bright |
| Charge | : Anionic |

Hard Protein Binder suitable for glossy top coat for plated and glazed finishes.

GLAZE TOP LM 58 is ideally suited for use as final top coat in glazed finishes or final glossy polish. It gives leather a silky touch and bright appearance. It also improves resistance to acetone and allows plating at higher temperatures.

GLAZE TOP LM 58 may also be incorporated in resin finish to reduce the tack and improve gloss, dry & wet rub-fastness and print retention. It can be fixed in the usual manner with fixatives like formaline or crosslinkers.

Usage

Stir before use

| | | | | |
|------------------------------|---|-------|-------|-----------------------|
| ▪ Glaze Finish (Top Coat) | : | 150 | parts | Glaze Top LM 58 |
| | | 50 | parts | Protop 18 |
| | | 3 | parts | Xama 7 |
| | | 750 | parts | Water |
| ▪ Glaze Finish (Season Coat) | : | 30 | parts | Glaze Top LM 58 |
| | | 970 | parts | Normal Season Mixture |
| ▪ Resin Finish | : | 40-60 | parts | Glaze Top LM 58 |
| | | 950 | parts | Normal Season Mixture |

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Prevent from freezing

Use Gloves / Ensure Ventilation



Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.