

GLOVOL AS 29

Characteristics

Composition	: Sulphochlorinated Aliphatic Hydrocarbon & Natural Oils
Appearance	: Light Brown Oily Liquid
Active Content	: 50 ± 1%
pH (1 : 10)	: 7.0 ± 0.5
Charge	: Anionic
Stability	: High
Light Fastness	: Excellent

Suggested Application

- ✓ Mainly chrome tanned gloving leathers

REACH COMPLIANT



Green-Trek- Compliant

À symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Store in dry place

Use Gloves / Ensure Ventilation



Universal Synthetic Fatliquor to be used as anionic combination component.

GLOVOL AS 29 is an ideal component for fatliquoring recipes that require an efficient synthetic component for deep penetration in leather. It is particularly suited for the production of white industrial gloving leathers where high percentage of fatliquor is required. It provides internal lubrication to the treated leathers, without causing any grain looseness, instead leaves the grain of leather soft, elastic, whiter and well lubricated.

GLOVAL AS 29 exhibits very good lightfastness and has no offensive odour. Slight bleaching property of Glovol AS 29 helps in reducing the chrome colour of leather which is advantageous to industrial gloving or white / pastel coloured leathers.

Usage

■ Industrial Gloving	Fatliquoring	6.0% Glovol AS 29
		8.0% Nouvol SR 4.0% Glovol HSN
■ Goat Gloving	Fatliquoring	6.0% Glovol AS 29
		3.0% Maradol C
		5.0% Nouvol LS 55
		3.0% Nouvol PK 4.0% Nouvol SR

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.