

## NOUVOL LS 55

## Characteristics

Composition	: Phospholipids and Anionic Emulsifiers
Appearance	: Reddish Yellow Paste
Active Content	: 52 ± 1%
pH (1 : 10)	: 8,0 ± 0,5
Emulsions	: Opalescent
Solubility	: Good
Light Fastness	: Good

*General purpose, Lecithin fatliquor, for very soft articles requiring fullness & crushable handle.*

NOUVOL LS 55 makes the leather feel exceptionally lightweight, full, smooth and silky to touch on flesh as well as grain side. Depending on the quantity used the touch can be varied from silky to waxy. Treated leather will have outstanding softness, texture and a crushable handle required for very soft upholstery and garment leathers. It can also be used as a handle improver for nubuck.

Leathers also exhibit improved tensile, tear, crease and stitch-tear resistance. Nouvol LS 55 has good heat and light fastness properties and is an ideal choice for white or pastel upholstery. It also offers a good gravimetric fogging behaviour.

It can be used alone as a single fatliquor for very soft and light weight articles but more often as a companion fatliquor in order to achieve the desired properties. Excellent results are obtained by combining it with phosphorated derivatives like Nouvol PK / Luber SAS. Generally compatible with all anionic products.

Usage

To the required quantity of Nouvol LS 55, add slowly three times of its own weight of water at 60°C, while stirring constantly.

▪ Cow Nappa	Fatliquoring	6.0% Nouvol LS 55 6.0% Nouvol PK 3.0% Maradol C 3.0% Luber G 60
▪ Sheep Nappa	Fatliquoring	5.0% Nouvol LS 55 2.0% Luber SAS 6.0% Nouvol PK
▪ Cow Softy	Fatliquoring	2.0% Luber G 60 3.0% Luber SN 2.0% Nouvol LS 55 1.0% Maradol C
▪ Buff Upholstery	Fatliquoring	4.0% Nouvol LS 55 8.0% Nouvol PK 3.0% Maradol C 3.0% Luber SAS

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.

## Suggested Application

- ✓ Garments
- ✓ Upholstery
- ✓ Double face

## REACH COMPLIANT



## Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.  
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Store in dry place

Use Gloves / Ensure Ventilation

