

## ACRIL-M Y 26

## Characteristics of Emulsion

|                       |                          |
|-----------------------|--------------------------|
| Appearance            | : Thin Opalescent Liquid |
| Nature                | : Polyacrylate in Water  |
| Charge                | : Anionic                |
| Solid Content         | : 20 ± 1%                |
| pH (Without Dilution) | : 8.0 ± 0.5              |
| Mechanical Stability  | : Good                   |
| Reaction with Ammonia | : Does Not Thicken       |

## Characteristics of Film

|                       |                         |
|-----------------------|-------------------------|
| Appearance            | : Clear and Transparent |
| Elasticity            | : Very Soft             |
| Tack Level            | : Low                   |
| Light Fastness        | : Excellent             |
| Cold-crack Resistance | : Good (minus 10°C)     |

## REACH COMPLIANT



## Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °C to 35 °C in original pack, well-sealed & stored.  
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non Flammable

Avoid direct contact with skin



Prevent from freezing

Use Gloves / Ensure Ventilation



*Micro fine, very soft acrylic co-polymer dispersion suitable for Impregnation of full grain leathers.*

ACRIL-M Y 26 is a very soft, micro fine particle sized resin dispersion with a characteristic of very good penetration on full grain leathers. It improves the break of soft, full grain leather by adequate grain filling without over stiffening the leather. It can also be combined with Acril-m Y 62 for corrected grain leather to optimise penetration when used with penetrator Luber 150.

ACRIL-M Y 26 produces clear and transparent film. It provides a soft, fine & uniform grain break, improves filling of loose portions, imparts mellow handle and hold up of subsequent coats. Being a highly penetrating product, it is useful as a tack free component in base coat formulations and is an excellent ingredient in light natural finishes.

Usage

|                    |   |  |
|--------------------|---|--|
| ▪ F/G Impregnation | : | 250 parts Acril-m Y 26<br>350 parts Water<br>100 parts Luber 150   |
| ▪ Season Coat      | : | 100 parts Pigment – Nano Series<br>100 parts Acril-m X 01<br>150 parts Acril-m Y 26<br>50 parts Urez 894<br>40 parts Filler WTD<br>40 parts Protop SP<br>520 parts Water |
| ▪ C/G Impregnation | : | 200 parts Acril-m Y 26<br>100 parts Acril-m Y 26<br>650 parts Water<br>50 parts Luber 150  |

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.