

GOAT LINING : RESIN FINISH : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Urez 899	150	100				1. 1 X Coat, plate at 80° C, 50 kg/ sq.cm. 2. 1 Pad Coats, Dry well, Goat Hair Cell Plate at 80° C, 50 Kg., 3 X Coats, Sand Blast at 80° C, 100 Kg, 1X Coat. 3. 2 X Coat, Dry well, Contilux.
2	Luber 205	50					
3	Primer PFR	50	20				
4	Water	700	400	150			
5	Nano Black 12	50	100				
6	Protop 18		50				
7	Compact 24		50				
8	Filler 12 / 61		80				
9	Acril-m X 01		150				
10	Acril-m S 60		50				
11	Haquatop 328			100			
12	Finish M 45	10	10	5			
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :

Code :

Pn = Hair Cell Print

Pr = Emboss •C

Po = Polish

RB = Rebuff

P = Plate •C/Bar

Vd = Vacuum Dry

M = Dry Drum (Mill)

O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission