

GOAT SHOE UPPER - 1 : RESIN FINISH : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	PUD 40 KT	150					1. 1 X coat, plate at 80°C, 50 kg. / sq. cm. 2. 2 X Coats, Dry well, Plate at 80° C, 50 Kg, 2 - 3X Coats. 3. 2 X coat, dry well, Contilux.
2	Luber 150	50					
3	Brillento 91 KT	50					
4	Water	750	500	100			
5	Nano Black Super		80				
6	Protop SP		50				
7	Compact 24		50				
8	Filler 12 / 61		50				
9	Acril-m X 79 / 60		50				
10	Acril-m S 8/1		100				
11	Urez 891		50				
12	Tuf Cryl VSF		50				
13	Hicalac 312			100			
14	Sansallon W			10			
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :

Code :

Pn = Hair Cell Print

Pr = Emboss •C

Po = Polish

RB = Rebuff

P = Plate •C/Bar

Vd = Vacuum Dry

M = Dry Drum (Mill)

O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission