

GOAT SHOE UPPER -2 : IMITATION GLAZED : BORDEAUX

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Urez 899	150					1. 1 X coat, plate at 80° C, 50 kg/ sq.cm. or Polish.
2	Luber 150	50					
3	Celina P 73	100					
4	Novolene Bordeaux	50	60				2. 2 X Coats, Dry well, Plate at 80° C, 50Kg, 2 - 3X Coats.
5	Water	650	450	20			
6	Nano Pigment Mix		40				3. 1 X coat, dry well, Contilux.
7	Protop SP		100				
8	Glaze Top N		50				
9	Filler 50		50				
10	Acrl-m X 79 / 60		100				
11	Urez 891		50				
12	Urez 785 G			100			
13	Glaze Top LM 58			10			
14	Crosslinker			5			
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :

Code :

Pn = Hair Cell Print

Po = Polish

P = Plate •C/Bar

M = Dry Drum (Mill)

Pr = Emboss •C

RB = Rebuff

Vd = Vacuum Dry

O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission