

GOAT SHOE UPPER -3 : GLAZED : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	PUD 40 KT	100					1. 1 X Coat, plate at 80° C, 50 kg. / sq. cm. 2. 2 X Coats, Dry well, Glaze Lightly or Plate at 90°C, 50 Kg, 2-3X Coats. 3. 2 X coat, dry well, Fix with Formalin or Crosslinker, Glaze, Contilux at 110° C.
2	Brillento 91 KT	50					
3	Cationic Black Dye	50					
4	Water	750	700	850			
5	NovolenePR Black		50				
6	Nano Black Super		50				
7	Protop 18		150				
8	Glaze Top EC		50				
9	GlazEx 72			100			
10	Glaze Top LM 58			50			
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :

Code :

Pn = Hair Cell Print

Po = Polish

P = Plate •C/Bar

M = Dry Drum (Mill)

Pr = Emboss •C

RB = Rebuff

Vd = Vacuum Dry

O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission