

LEATHER FINISH 235

Characteristics

Appearance	: Very Fine Emulsion
Nature	: PU based resin
Solid Content	: 35 ± 1%
pH (10% Sol.)	: 9.0 ± 0.5
Density	: 1.04
Charge	: Anionic
Gloss	: Medium
Mechanical stability	: Good
Reaction with ammonia	: None

Characteristics of film

Appearance	: Transparent
Elongation	: 10 (1 Min. - 10 Max.)
Gloss	: 08 (1 Matt -10 Glossy)
Shore Hardness	: 04 (1 Softest - 10 Hardest)
Light Fastness	: Good
Cold-crack Resistance	: Good

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Store in dry place

Use Gloves / Ensure Ventilation

*Medium soft resin finish for leather.*

LEATHER FINISH 235 is a medium soft PU based Resin having good water and solvent resistance. The leather may be finished with the product, alone or alongwith other ingredients like pigments, acrylics and waxes It's good anchorage characteristic makes it ideal for use in sophisticated leathers like garments, softies and upholstery.

Usage

Sheep Garment:	100 parts Pigment – Nano Series 50 parts Glaze Top N 30 parts Wax 16 S 520 parts Water 125 parts Leather Finish 235 75 parts Acril-m M 701 100 parts Urez 899
Goar Shoe Uppers:	100 parts Pigment – Nano Series 30 parts Protop 18 30 parts Filler WTD 50 parts Filler 12/61 530 parts Water 100 parts Leather Finish 235 100 parts Acril-m S 8/1 50 parts Urez 894 10 parts Liquid NH ₃

IMPORTANT: Protect from freezing.

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.