

ACRIL-M S 6072

Characteristics of Emulsion

Appearance	: Semi-Transperant Milky Emulsion
Nature	: Polyacrylate Dispersion
Solid Content	: 36 ± 1%
pH (10% Sol.)	: 5.0 ± 0.5
Charge	: Anionic
Mechanical Stability	: Very good
Reaction with Ammonia	: Thickens Slightly

Characteristics of Film

Appearance	: Transparent
Tensile Strength	: 6.8 Mpa / 992 PSI
Elongation	: 440%
Gloss	: 68 BYK Gardner
Shore A Hardness	: 50 (Zwick/Roell)
Sticking Level	: Low
Light Fastness	: Good
Cold-crack Resistance	: Good (minus 10°C)

REACH COMPLIANT



Green-Trek- Compliant

a symbol of our commitment to sustainable technologies

Storage : Store between +5 °c to 35 °c in original pack, well-sealed.
Shelf-life : Product is stable for 6 months from the date of production.



Non Flammable / Keep Flames Away

Store Indoors



Protect From Snow

Use Gloves/Ensure Ventilation



Micro Binder having higher solids with very fine particle size, provides a naked look with minimal resinous loading.

ACRIL-M S 6072 is a microfine self crosslinking acrylic polymer suitable for a wide range of leathers. Due to its fine particles it penetrates well for good adhesion while maintaining flexibility and builds good cold-crack resistance. It can be an ideal soft component of a base coat for grain tightening application on full grain or corrected grain leathers.

Unlike other micro binders, ACRIL-M S 6072 has higher solids as compared to other micro binders, thus it imparts good mechanical stability and flow out. It also affords excellent plating and embossing characteristics. It may be used alone or in combination with other binders like Acril-m X 858, Acril-m S-60 etc. and normally provides better fastness, increased extensibility and flexibility .

Usage

- Corrected Grain :
 - 150 parts Pigment - Nano Series
 - 150 parts Acril-m S 6072
 - 100 parts Acril-m S 60
 - 50 parts Filler WTD
 - 50 parts Filler 12/61
 - 50 parts Glaze Top EC
 - 50 parts Urez 899
 - 400 parts Water
- Nappa :
 - 100 parts Pigment - Nano Series
 - 100 parts Acril-m S 6072
 - 100 parts Acril-m X 858
 - 30 parts Wax 16/S
 - 30 parts Glaze Top N
 - 20 parts Luber 205
 - 50 parts Urez 899
 - 570 parts Water

IMPORTANT: PROTECT FROM FREEZING.

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.