

BLACK 33 KT

Characteristics of Emulsion

Appearance	: Jet Black / Opaque / Liquid
Solid Content	: 30 ± 1%
pH (10 % sol.)	: 4.0 - 4.5
Mechanical Stability	: Good
Viscosity -CPS	: 200 Max.

REACH COMPLIANT



Green-Trek- Compliant

A symbol of our commitment to sustainable technologies

Storage : Store between +5 ' c to 35 ' c in original pack, well-sealed & stored.
Shelf-life : Product is stable for 6 months from the date of production / Invoice.



Non flammable

Avoid direct contact with skin



Store in dry place

Use Gloves / Ensure Ventilation



Jet black, aqueous pigment dispersion for use In cationic finishes.

BLACK 33 KT is used in high performance basecoat formulations, particularly for nappa garments, shoe upper leather or " Nappalan " finishes. It offers outstanding tinctorial strength, UV lightfastness and colour brilliance. The choice of dispersant in the system can afford good resistance to washing, and ensures no bleeding or migration into PVC.

The use of Black 33 KT pigment together with cationic auxiliaries of our range makes it possible to produce very soft finishing with a natural aspect without overloading grain. Also the cationic finishing system based on Black 33 KT resolves the adhesion and rubbed grain problem. It is compatible with only cationic auxiliaries. Care should be taken in the in the blend ratio of the pigments used so that the desired physical properties are achieved.

Usage

Stir before use 

Sheep Nappa:	30 Parts	Black 33 KT
	90 Parts	Brillento 91 KT
	30 Parts	Filler KT
	30 Parts	Celina 34 KT
	670 Parts	Water
	120 Parts	PUD 40 KT
	30 Parts	PUD 48 KT

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.