

ACRIL-M S 6755

Characteristics of Emulsion

Appearance	: Creamish Yellow Emulsion
Nature	: Polyacrylate Dispersion
Solid Content	: 36 ± 1%
pH (10% Sol.)	: 7.0 ± 0.5
Charge	: Anionic
Mechanical Stability	: Very Good
Reaction with Ammonia	: Increase in Viscosity

Characteristics of Film

Appearance	: Transparent
Tensile Strength	: 4.02 Mpa / 583 PSI
Elongation	: 520%
Gloss	: 73 BYK Gardner
Shore A Hardness	: 46 (Zwick/Roell)
Light Fastness	: Good
Cold-crack Resistance	: Good (minus 10°C)

REACH COMPLIANT



Green-Trek- Compliant

a symbol of our commitment to sustainable technologies

Storage : Store between +5 °C to 35 °C in original pack, well-sealed.
Shelf-life : Product is stable for 6 months from the date of production.



Non Flammable / Keep Flames Away

Store Indoors



Protect From Snow

Use Gloves/Ensure Ventilation



High Gloss, Medium Soft Acrylic Binder that provides tough adhesion, brilliant look and dry / wet rub fastness to the finish.

ACRIL-M S 6755 is a general purpose, medium soft binder and can be used extensively for various type of leathers that require high gloss and a slight stiffer handle as compared to other medium soft acrylics. It can cater to season coats that provide good coverage and body to the finishes. Leather finished with Acril-m S 6755 exhibits good fastness to rubbing, good cold-crack, a smoother and uniform look.

ACRIL-M S 6755 has good plate release and printing properties without a residual tack. It may be used alone or combined with other acrylic binders provided they are not cationic in nature. It can be blended with Acril-m X 858 or Acril-m S 8/1 for adjusting gloss and flexibility for more aniline looks.

Usage

- Corrected Grain : 150 parts Pigment - Nano Series
150 parts Acril-M S 6755
100 parts Acril-m X 79/60
50 parts Filler WTD
50 parts Filler 12/61
50 parts Glaze Top EC
50 parts Urez 894
400 parts Water
- Sheep Nappa : 80 parts Pigment - Nano Series
100 parts Acril-m S 6755
100 parts Acril-m S 8/1
30 parts Filler 50
30 parts Glaze Top N
20 parts Luber 205
50 parts Urez 899
590 parts Water

IMPORTANT: PROTECT FROM FREEZING.

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.