

ACRIL-M Y 62

Characteristics of Emulsion

Appearance	: Slightly Opalescent Liquid
Nature	: Polyacrylate Dispersion
Solid Content	: 30 ± 1%
pH (10% Sol.)	: 6.5 ± 0.5
Density	: 1.02
Charge	: Anionic
Mechanical Stability	: Good
Reaction with Ammonia	: Slight Thickening

Characteristics of Film

Appearance	: Clear and Transparent
Elasticity	: Medium-hard
Sticking Level	: None
Light Fastness	: Excellent
Cold-crack Resistance	: Medium

REACH COMPLIANT



Green-Trek- Compliant

a symbol of our commitment to sustainable technologies

Storage : Store between +5 °C to 35 °C in original pack, well-sealed.
Shelf-life : Product is stable for 6 months from the date of production.



Non Flammable / Keep Flames Away

Store Indoors



Protect From Snow

Use Gloves/Ensure Ventilation



Acrylic Co-Polymer, medium soft emulsion resin for surface impregnation of corrected grain leathers to improve break - especially shoe upper leather.

ACRIL-M Y 62 is a fine particle sized aqueous impregnating resin designed for shoe uppers, particularly corrected type where resistance to acetone and toluene is desired. It gives good filling properties and a smooth pull up during lasting. The leathers achieve a mellow handle, improved scuff resistance with excellent grain break properties.

ACRIL-M Y 62 while applying has to be mixed with a suitable penetrator like Luber 205 or Luber 150. It may also be used in a small quantity in base coat applications for promoting the adhesion of finish.

Usage

▪ Impregnation	:	350 parts Acril-m Y 62
		50 parts Luber 205 / Luber 150
		600 parts Water
▪ Impregnation	:	200 parts Acril-m Y 62
		100 parts Acril-m Y 93
		50 parts Luber 205 / Luber 150
		650 parts Water
▪ Base Coat	:	100 parts Pigment - Nano Series
		100 parts Acril-m X 858
		100 parts Acril-m X 79/60
		50 parts Acril-m Y 62
		50 parts Filler WTD
		50 parts Filler 12/61
		20 parts Luber 205
		530 parts Water

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.