

## GLAZE TOP LM 58

### Characteristics of Emulsion

Appearance	: Straw like (can change the color)
Basic Ingredients	: Casein
Solid Content	: 10 ± 1%
pH (10% Sol.)	: 8.5 ± 0.5
Nature	: Hard Protein
Film Appearance	: Transparent, bright
Charge	: Anionic

### REACH COMPLIANT



### Green-Trek- Compliant

a symbol of our commitment to sustainable technologies

Storage : Store between +5 °C to 35 °C in original pack, well-sealed.  
 Shelf-life : Product is stable for 6 months from the date of production.



Non Flammable / Keep Flames Away

Store Indoors



Protect From Snow

Use Gloves/Ensure Ventilation



**Hard Protein Binder suitable for glossy top coat for plated and glazed finishes.**

**GLAZE TOP LM 58** is ideally suited for use as final top coat in glazed finishes or final glossy polish. It gives leather a silky touch and bright appearance. It also improves resistance to acetone and allows plating at higher temperatures.

**GLAZE TOP LM 58** may also be incorporated in resin finish to reduce the tack and improve gloss, dry & wet rub-fastness and print retention. It can be fixed in the usual manner with fixatives like formaline or crosslinkers.

### Usage

Stir before use

▪ Glaze Finish (Top Coat)	:	150 parts	Glaze Top LM 58
		50 parts	Protop 18
		3 parts	Xama 7
		750 parts	Water
▪ Glaze Finish (Season Coat)	:	30 parts	Glaze Top LM 58
		970 parts	Normal Season Mixture
▪ Resin Finish	:	40-60 parts	Glaze Top LM 58
		950 parts	Normal Season Mixture

Note: Suggested formulations are only for guidance and necessary modifications must be made to achieve a particular result.