

**COW AUTOMOTIVE UPHOLSTERY : RESIN FINISH : OFF WHITE**

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Nano Pigment Mix	150					1. 1 R/C or Airless Spray, Leave O/N, Print at 90°C / 100 Kg. 2 X Coats, Dry well.  2. 1 R/C or Airless Spray, Dry well, Stake, Dry Mill for 4 Hrs. 1 X coat, Stake and Toggle.
2	Uphin 100	350					
3	Acril-m X 79 / 60	100					
4	Water	300	200				
5	Urez 785 M		750				
6	Crosslinker		20				
7	Luber 150	30					
8	Sensallon W	20	20				
9							
10							
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
<b>Code :</b>			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

**Suggested products comply with REACH and free from:**

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission