

**COW FURNITURE UPHOLSTERY : RESIN FINISH : BLACK**

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Nano Black 12	80					1. 2 Pad Coats, Dry Well, Dry mill plate at 80 °C / 200 Kg., 3 X Coats, Dry well.  2. 1 X Wet Coat, Dry Well, Dry Mill for 4 Hrs. Contilux. Stake, and Toggle, 1 X Coat Light.
2	Nano Black Super	70					
3	Compact 24	200					
4	Wax 16/S	50					
5	Sensallon W	10					
6	Modifier WS	20					
7	Glaze Top N	50					
8	Finish M 45	10					
9	Luber 150	8					
10	Acil-m S 8/1	120					
11	Acil-m X 858	120					
12	Urez 898	50					
13	Water	360	20				
14	Crosslinker		5				
15	Regella Top M1		30				
16	Urez 785 G		70				
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
<b>Code :</b>			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

**Suggested products comply with REACH and free from:**

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission