

COW LEATHER GOODS : RESIN FINISH : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Black 33 KT	20					Snuff the leather with 600 grit paper, de-dust properly. 1. 2 X Coat, Dry well, Kiss plate. 2. 2 X Coats, Dry well, Plane Plate at 80°C, 50 Kg./cm ² ., 3 X Coats. 3. 1 X Coat, Dry well, Contilux. 4. 1 X coat, Stake and Toggle.
2	Cationic Black Dye	60					
3	Filler KT	30					
4	Brillento 91 KT	100					
5	PUD 40 KT	150					
6	PUD 48 KT	30					
7	Celina 34 KT	30			30		
8	Water	580	500	190	400		
9	Nano Deep Black		80				
10	Novolene PR Black		20				
11	Acril-m X 79 / 60		50				
12	Acril-m S 8/1		100				
13	Urez 898		100				
14	Protop SP		50				
15	Filler 50		50				
16	Haquatop 328			100			
17	Finish M 45			10	70		
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission