

COW LINING : RESIN FINISH : GREY

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Nano Series Pigment	120					1. 3 x Coats, Fine H/c Plate at 80 °C / 150 Kg., 3 x coats, Super Fine H/C, 2 x coats. 2. 2 x Coat, Sand Blast plate at 90 °C/ 100 Kg. 3. 1 x Coat.
2	Acrl-m X 79 / 60	100					
3	Acrl-m X 858	100					
4	Compact 24	200					
5	Neowax ST	60					
6	Glaze Top EC	30					
7	Filler 12 / 61	50					
8	Luber 150	15					
9	Finish M 45	10		50			
10	Hicalac 316		100				
11	Water	415	100	950			
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION : Shuff the crust two times with 240 grit paper and once with 320 grit before finishing.

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission