

COW SHOE UPPER - 1 : ANILENE : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Black 33KT	30					1. 2 X Coat, Dry well, Kiss plate. 2. 3 X Coats, Dry well. 3. 1 X Coat, Dry well, Dry Shave, Contilux. 4. 1 X Coat, Stake and Toggle.
2	Cationic Black Dye Solution	20					
3	Filler KT	20					
4	Celina 34 KT	30			40		
5	Brillento 91 KT	100					
6	PUD 40 KT	100					
7	Water	700	510	200	250		
8	Nano Black Super		50				
9	Novolene PR Black		30				
10	Protop 18		40				
11	Glaze Top N		20				
12	Filler 12/61		50				
13	Acril-m M 701		50				
14	Acril-m S 60		50				
15	Acril-m X 858		100				
16	Wax 16/S		30				
17	Urez 891		50				
18	Luber 150		20				
19	Haquatop 328			100			
20	Finish M 45			8	10		
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission