

COW SHOE UPPER - 8 : OIL PULL UP : DARK BROWN

FINISHING FORMULATION & PROCESS							
	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Waxol 420	100					1. 1 R/C, Leave O/N, Plane plate at 120 °C / 50 Kg., 1 light spray, dry well. 2. 2 - 3 light x coats, Fix, Dry well fix & Contilux at 100°C / 40 Kg./cm ² .
2	Glaze Top N		100				
3	Protop SP		50				
4	Urez 899		100				
5	Luber 150		50				
6	Water	50	700				
7	Nano Pigment		10				
8	Novolene PR Dye		25				
9							
10							
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION: Buff twice with 320 grit paper on both sides before finishing.

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission