

COW SHOE UPPER - 9 : OIL PULL UP-CRAZY HORSE : BROWN

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Luber LMC	100					1. 1 R/C, Leave O/N, Plane Plate at 100°C/50Kg. 1 light spray, dry well. 2. 2 - 3 light x coats, 3. 1 x coat, Fix, Dry well Fix & Contilux at 100°C / 40 Kg./cm ² .
2	Glaze Top N		75	100			
3	Protop 18		75	100			
4	Dye Solution / Novolene PR		25				
5	Urez 899		100				
6	Water		725	800			
7							
8							
9							
10							
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION: Buff twice with 320 grit paper on both sides before finishing.



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission