

BUFFALO UPHOLSTERY - 2 : RESIN FINISH : BLACK

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Nano Black 12	150					1. 1 R/C or Airless Spray, Leave O/N, Print at 90°C / 150 Kg. 2 X Coats, Dry well. 2. 1 R/C or Airless Spray, Dry well, Stake, Dry Mill for 4 Hrs. 1 X coat, Stake and Toggle.
2	Uphin 21 WX	500					
3	Water	100	50				
4	Urez 785 M		100				
5	Urez 785 G		50				
6	Crosslinker		5				
7	Tuf-Cryl VSF	100					
8							
9							
10							
11							
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission