

## COW INDUSTRIAL GLOVING THICKNESS : 1.0 - 1.2 MM

RETANNING - DYEING - FATLIQUORING					
OPERATIONS	PRODUCT	°C	%	RUN	REMARKS
Washing	Water	30	200		
	Oxalic Acid		0.5		
	Sinto ALX		0.5	30	D/W
	Water	30	100		
	Pot. Permanganate		0.2	30	
	+ Sodium Bi Sulphite		1.0	30	
Neutralisation	+ Oxalic Acid		1.5	40	D/W
	Water	30	150		
	Sodium Formate		2.0	30	
+ Sodium Bi Carbonate		2.0	30		pH 6.0 Drain / Wash
Retanning	Water	60	100		
Dyeing	Glovol HSN		5.0		
Fatliquoring	Uphol MX		5.0		
	Glovol AS 29		4.0		
	Neophol CX		4.0	90	30 + 60
	TiO <sub>2</sub>		1.0	20	
	Formic Acid		2.0	50	10 + 10 + 30
	TiO <sub>2</sub>		1.0	30	
	Formic Acid		0.5	30	Rinse, Pile

MACHINE OPERATIONS : Pile, wet nail o/n, Hang Dry when in sammed condition, stake, dry mill.



Committed to sustainable technologies

Code :					
D/W/D = Drain / Wash / Drain	Chk = Check	Ø = Cross Section	+	= Add	O/N = Over Night
Run = Time in Minutes	Pdr = Powder	Vd = Vacuum Dry	L O/N	= Leave Over Night	

### Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI, PCP, Cresols
- AP/APEO, SCCP, M CCP
- Forbidden Amines, Bisphenol
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, Cresols, PCP/OPP