

**COW SOFTY - FINE MILLED      THICKNESS : 0.9 - 1.0 MM**

RETANNING - DYEING - FATLIQUORING					
OPERATIONS	PRODUCT	°C	%	RUN	REMARKS
Washing	Water	30	200		
	Formic Acid		0.5		
	Sintol ALX		0.5	60	D/W/D
Rechroming	Water	30	100		
	Relugan GT 50		1.5	30	
	+ Catanol DW		2.0	30	
	+ BCS Powder		6.0		
	+ Sodium Formate		0.5	60	
	+ Maradol C		1.0	30	
	+ Sodium Bi Carbonate		0.5	60	Chk. pH 4.0, D/W/D
Neutralisation	Water	30	200		
	Syntan NT		1.0	20	
	+ Sodium Bi Carbonate		1.5	50	pH 5.0
	+ Luber SAS		2.0	30	
	+ Syntan PR		5.0	30	L O/N, D/W/D
Retanning	Water	60	100		
Dyeing	Black dye		2.0		
Fatliquoring	Syntan OM		1.0		
	Syntan PMX		3.0		
	Syntan SPX		2.0	40	Chk ø
	+ Maradol C		4.0		
	Uphol PFK		4.0		
	Luber SN		4.0		
	Luber SAS		3.0		
	Neophol S 66		3.0	90	Chk Exhaustion
	+ Formic Acid		1.5	60	(10 + 10 + 40), Drain

**MACHINE OPERATIONS :** Pile O/N., Set Lightly, Hang Dry, Condition, Stake, Dry Mill & Toggle



Committed to sustainable technologies

**Code :**

D/W/D = Drain / Wash / Drain    Chk = Check    ø = Cross Section    + = Add    O/N = Over Night  
Run = Time in Minutes    Pdr = Powder    Vd = Vacuum Dry    L O/N = Leave Over Night

**Suggested products comply with REACH and free from:**

- Heavy Metals, Cr. VI, PCP, Cresols
- AP/APEO, SCCP, MCCP
- Forbidden Amines, Bisphenol
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, Cresols, PCP/OPP