COW SPLIT UPPER THICKNESS : 0.9 - 1.0 MM

RETANNING - DYEING - FATLIQUORING

OPERATIONS	PRODUCT	°C	%	RUN	REMARKS
Washing	Water	30	200		
	Sintol ALX		1.0	60	D/W/D
Rechroming	Water	30	200		
	BCS Powder		4.0		
	Chrome Syntan		4.0		
	Sodium Formate		1.0	30	pH 4.0, Drain
Neutralisation	Water		150		
	Sodium Formate		1.0		
+	Ammonium Bi Carb.		0.8	60	pH 5.0, D/W/D
Retanning	Water	30	250		
Dyeing	Retan 38		2.0	20	
Fatliquoring +	Syntan PM		5.0		
	GS Powder		3.0		
	Tanone EB/L		2.0		
	Syntan R - MF		2.0	40	
+	Syntan OM		1.0	10	
+	Black Dye		3.0	30	Chk ø
+	Luber G 60		2.0		
	Luber SN		2.0		
	Nouvol LS 55		2.0		
	Luber NF		1.0	45	Chk Exhaustion
+	GS Powder		2.0	20	
+	Formic Acid		3.0	60	(10 + 10 + 40), D/W/D

MACHINE OPERATIONS : Pile O/N., Samm, Vd, Hang Dry, Condition, Stake & Toggle.

Green-Trek

Committed to sustainable technologies

Code :

D/W/D = Drain / Wash / Drain Chk = Check Ø = Cross Section + = Add O/N = Over Night
Run = Time in Minutes Pdr = Powder Vd = Vacuum Dry L O/N = Leave Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI, PCP, Cresols
- AP/APEO, SCCP, MCCP
- Forbidden Amines, Bisphenol
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, Cresols, PCP/OPP