

SHEEP LINING : RESIN FINISH : NATURAL

FINISHING FORMULATION & PROCESS							
S.No.	PRODUCT	1	2	3	4	5	PROCESS / REMARKS
1	Urez 899	150	50				1. 1 X Coat, plate at 80° C, 50 kg/ sq.cm. 2. 2 X Coats, Dry well, fine Hair Cell Plate at 80° C, 50 Kg, 2 - 3 X Coats. 3. 2 X Coat, Dry well, Contilux.
2	Luber 150	100					
3	Water	400	500	100			
4	Nano Pigment Mix		100				
5	Protop 18		50				
6	Uphin 21 WX		50				
7	Filler 12 / 61		50				
8	Acrl-m X 79/60		100				
9	Acrl-m S 8/1		100				
10	Hicalac 316			100			
11	Sensallon W		10	20			
12							
13							
14							
15							
16							
17							
18							
19							
20							
21							
22							
23							
24							

APPLICATION :

REMARKS:



Committed to sustainable technologies

REMARKS :			
Code :			
H/C = Hair Cell Print	Po = Polish	P = Plate •C/Bar	M = Dry Drum (Mill)
Pr = Emboss •C	RB = Rebuff	Vd = Vacuum Dry	O/N = Over Night

Suggested products comply with REACH and free from:

- Heavy Metals, Cr. VI
- AP/APEO, SCCP, Phthalate
- Arylamines (Azo group), Forbidden Amines
- PFCs, PAHs, PFOs, PCB
- Formaldehyde, NMP, NEP, DMF
- Complies with VOC emission